



## Specification of Magnetic Powder Core

Mirrack  
www.mirrack.com(CN)  
www.mirrack.com.cn (EN)

Part Number	Product Series	Permeability (u)	$A_L$ (nH/N <sup>2</sup> )	Coating Color	Coating Material	Coating Breakdown Voltage
MKS102-075	MKS	75	40±8%	Black	Epoxy	800Vac / 0.5mA / 3sec
Description	Toroidal Sendust Core					

### Core Dimensions

Dimensions	Before Coating		After Coating		Min / Max
	inch	mm	inch	mm	
OD	0.400	10.20	0.425	10.80	Max
ID	0.200	5.08	0.180	4.57	Min
HT	0.156	3.96	0.181	4.60	Max



### Physical Characteristics & Packaging

Path Length Le (cm)	Cross Section Ae (cm <sup>2</sup> )	Core Volume Ve (cm <sup>3</sup> )	Window Area Wa (cm <sup>2</sup> )	Weight (g)	Box QTY (pcs)
2.380	0.100	0.238	0.164	1.42±5%	12000

### Electrical Features (@25°C±2°C)

Test Item	Condition	Value (Typical)
Inductance	∅0.5mm, 25TS, 100KHz, 1.0V, 0A	25uH±8%
DC-Bias	∅0.5 mm, 25TS, 100KHz, 1.0V, I <sub>DC(100 Oe)</sub> = 7.61 A	38% Min
Core Loss	∅0.5mm, 25TS, 50KHz, 1000Gauss	320mW/cm <sup>3</sup> Max
Hi-Pot	800Vac, 0.5mA, 3 sec	PASS

### DC Bias Curves

