



Specification of Magnetic Powder Core

Mirrack
www.mirrack.com(CN)
www.mirrack.com.cn (EN)

Part Number	Product Series	Permeability (u)	A_L (nH/N ²)	Coating Color	Coating Material	Coating Breakdown Voltage
MKS203-075	MKS	75	41±8%	Black	Epoxy	800Vac / 0.5mA / 3sec
Description	Toroidal Sendust Core					

Core Dimensions

Dimensions	Before Coating		After Coating		Min / Max
	inch	mm	inch	mm	
OD	0.800	20.30	0.830	21.10	Max
ID	0.500	12.70	0.475	12.07	Min
HT	0.250	6.35	0.286	7.11	Max



Physical Characteristics & Packaging

Path Length Le (cm)	Cross Section Ae (cm ²)	Core Volume Ve (cm ³)	Window Area Wa (cm ²)	Weight (g)	Box QTY (pcs)
5.090	0.226	1.150	1.410	7.2±5%	2400

Electrical Features (@25°C±2°C)

Test Item	Condition	Value (Typical)
Inductance	∅0.5mm, 50TS, 100KHz, 1.0V, 0A	102.5uH±8%
DC-Bias	∅0.5 mm, 50TS, 100KHz, 1.0V, $I_{DC(100 Oe)} = 8.144$ A	38% Min
Core Loss	∅0.5mm, 50TS, 50KHz, 1000Gauss	320mW/cm ³ Max
Hi-Pot	800Vac, 0.5mA, 3 sec	PASS

DC Bias Curves

