




## Specification of Magnetic Powder Core

Mirrack  
 www.mirrack.com(CN)  
 www.mirrack.com.cn (EN)

Part Number	Product Series	Permeability (u)	$A_L$ (nH/N <sup>2</sup> )	Coating Color	Coating Material	Coating Breakdown Voltage
MKS066-026	MKS	26	11 ± 8%	Black	Epoxy	800Vac / 0.5mA / 3sec
Description	Toroidal Sendust Core					

### Core Dimensions

Dimensions	Before Coating		After Coating		Min / Max
	inch	mm	inch	mm	
OD	0.260	6.60	0.285	7.24	Max
ID	0.105	2.67	0.085	2.16	Min
HT	0.100	2.54	0.125	3.18	Max



### Physical Characteristics & Packaging

Path Length Le (cm)	Cross Section Ae (cm <sup>2</sup> )	Core Volume Ve (cm <sup>3</sup> )	Window Area Wa (cm <sup>2</sup> )	Weight (g)	Box QTY (pcs)
1.363	0.047	0.064	0.041	0.45 ± 5%	20000

### Electrical Features (@25°C ± 2°C)

Test Item	Condition	Value (Typical)
Inductance	∅0.5mm, 10TS, 100KHz, 1.0V, 0A	1.1uH ± 8%
DC-Bias	∅0.5 mm, 10TS, 100KHz, 1.0V, I <sub>DC(100 Oe)</sub> = 10.85 A	75% Min
Core Loss	∅0.5mm, 10TS, 50KHz, 1000Gauss	650mW/cm <sup>3</sup> Max
Hi-Pot	800Vac, 0.5mA, 3 sec	PASS

### DC Bias Curves

