



Specification of Magnetic Powder Core

Mirrack
www.mirrack.com(CN)
www.mirrack.com.cn (EN)

Part Number	Product Series	Permeability (u)	A_L (nH/N ²)	Coating Color	Coating Material	Coating Breakdown Voltage
MKS234-060	MKS	60	51±8%	Black	Epoxy	800Vac / 0.5mA / 3sec
Description	Toroidal Sendust Core					

Core Dimensions

Dimensions	Before Coating		After Coating		Min / Max
	inch	mm	inch	mm	
OD	0.928	23.60	0.956	24.30	Max
ID	0.567	14.40	0.542	13.77	Min
HT	0.350	8.89	0.382	9.70	Max



Physical Characteristics & Packaging

Path Length Le (cm)	Cross Section Ae (cm ²)	Core Volume Ve (cm ³)	Window Area Wa (cm ²)	Weight (g)	Box QTY (pcs)
5.880	0.388	2.280	1.490	14.0±5%	1600

Electrical Features (@25°C±2°C)

Test Item	Condition	Value (Typical)
Inductance	∅0.5mm, 50TS, 100KHz, 1.0V, 0A	127.5uH±8%
DC-Bias	∅0.5 mm, 50TS, 100KHz, 1.0V, I _{DC(100 Oe)} = 9.4 A	48% Min
Core Loss	∅0.5mm, 50TS, 50KHz, 1000Gauss	350mW/cm ³ Max
Hi-Pot	800Vac, 0.5mA, 3 sec	PASS

DC Bias Curves

