




## Specification of Magnetic Powder Core

Mirrack  
 www.mirrack.com(CN)  
 www.mirrack.com.cn (EN)

Part Number	Product Series	Permeability (u)	$A_L$ (nH/N <sup>2</sup> )	Coating Color	Coating Material	Coating Breakdown Voltage
MKS343-060	MKS	60	38±8%	Black	Epoxy	1.2KVac / 0.5mA / 3sec
Description	Toroidal Sendust Core					

### Core Dimensions

Dimensions	Before Coating		After Coating		Min / Max
	inch	mm	inch	mm	
OD	1.350	34.30	1.382	35.10	Max
ID	0.920	23.40	0.888	22.56	Min
HT	0.350	8.89	0.387	9.83	Max



### Physical Characteristics & Packaging

Path Length Le (cm)	Cross Section Ae (cm <sup>2</sup> )	Core Volume Ve (cm <sup>3</sup> )	Window Area Wa (cm <sup>2</sup> )	Weight (g)	Box QTY (pcs)
8.950	0.454	4.060	4.010	25.0±5%	441

### Electrical Features (@25°C±2°C)

Test Item	Condition	Value (Typical)
Inductance	∅1.0 mm, 50TS, 100KHz, 1.0V, 0A	95uH±8%
DC-Bias	∅1.0 mm, 50TS, 100KHz, 1.0V, $I_{DC(100Oe)} = 14.25$ A	48% Min
Core Loss	∅1.0mm, 50TS, 50KHz, 1000Gauss	350mW/cm <sup>3</sup> Max
Hi-Pot	1.2KVac, 0.5mA, 3 sec	PASS

### DC Bias Curves

