




Specification of Magnetic Powder Core

Mirrack
 www.mirrack.com(CN)
 www.mirrack.com.cn (EN)

Part Number	Product Series	Permeability (u)	A _L (nH/N ²)	Coating Color	Coating Material	Coating Breakdown Voltage
MKF343-026	MKF	26	16±8%	Blue	Epoxy	1.2KVac / 0.5mA /3sec
Description: Toroidal Si-Fe Core						

Core Dimensions

Dimensions	Before Coating		After Coating		Min / Max
	inch	mm	inch	mm	
OD	1.350	34.30	1.382	35.10	Max
ID	0.920	23.40	0.888	22.56	Min
HT	0.350	8.89	0.387	9.83	Max



Physical Characteristics & Packaging

Path Length Le (cm)	Cross Section Ae (cm ²)	Core Volume Ve (cm ³)	Window Area Wa (cm ²)	Weight (g)	Box QTY (pcs)
8.95	0.454	4.06	4.01	29.0±5%	441

Electrical Features (@25°C±2°C)

Test Item	Condition	Value (Typical)
Inductance	∅1.0 mm, 50TS, 100KHz, 1.0V, 0A	40uH±8%
DC-Bias	∅1.0 mm, 50TS, 100KHz, 1.0V, I _{DC(100 Oe)} = 13.04 A	88%Min
Core Loss	∅1.0mm, 50TS, 50KHz, 1000Gauss	820mW/cm ³ Max
Hi-Pot	1.2KVac, 0.5mA, 3 sec	PASS

DC Bias Curves

