



Specification of Magnetic Powder Core

Mirrack
 www.mirrack.com(CN)
 www.mirrack.com.cn (EN)

Part Number	Product Series	Permeability (u)	A _L (nH/N ²)	Coating Color	Coating Material	Coating Breakdown Voltage
MKF468-060	MKF	60	86±8%	Blue	Epoxy	1.5KVac / 0.5mA /3sec
Description Toroidal Si-Fe Core						

Core Dimensions

Dimensions	Before Coating		After Coating		Min / Max
	inch	mm	inch	mm	
OD	1.840	46.70	1.875	47.63	Max
ID	1.130	28.70	1.098	27.89	Min
HT	0.600	15.20	0.635	16.13	Max



Physical Characteristics & Packaging

Path Length Le (cm)	Cross Section Ae (cm ²)	Core Volume Ve (cm ³)	Window Area Wa (cm ²)	Weight (g)	Box QTY (pcs)
11.63	1.34	15.53	6.11	104±5%	125

Electrical Features (@25°C±2°C)

Test Item	Condition	Value (Typical)
Inductance	∅1.0 mm, 50TS, 100KHz, 1.0V, 0A	215uH±8%
DC-Bias	∅1.0 mm, 50TS, 100KHz, 1.0V, I _{DC(100 Oe)} = 18.51 A	70%Min
Core Loss	∅1.0mm, 50TS, 50KHz, 1000Gauss	620mW/cm ³ Max
Hi-Pot	1.5KVac,0.5mA, 3 sec	PASS

DC Bias Curves

