




Specification of Magnetic Powder Core

Mirrack
www.mirrack.com(CN)
www.mirrack.com.cn (EN)

Part Number	Product Series	Permeability (u)	A _L (nH/N ²)	Coating Color	Coating Material	Coating Breakdown Voltage
MKF777-075	MKF	75	85±8%	Blue	Epoxy	1.5KVac / 0.5mA /3sec
Description	Toroidal Si-Fe Core					

Core Dimensions

Dimensions	Before Coating		After Coating		Min / Max
	inch	mm	inch	mm	
OD	3.063	77.80	3.108	78.90	Max
ID	1.938	49.20	1.898	48.20	Min
HT	0.500	12.70	0.545	13.84	Max



Physical Characteristics & Packaging

Path Length Le (cm)	Cross Section Ae (cm ²)	Core Volume Ve (cm ³)	Window Area Wa (cm ²)	Weight (g)	Box QTY (pcs)
20.000	1.770	34.700	17.990	245±5%	64

Electrical Features (@25°C±2°C)

Test Item	Condition	Value (Typical)
Inductance	∅1.0 mm, 50TS, 100KHz, 1.0V, 0A	212.5uH±8%
DC-Bias	∅1.0 mm, 50TS, 100KHz, 1.0V, I _{DC(100 Oe)} = 31.84 A	55%Min
Core Loss	∅1.0mm, 50TS, 50KHz, 1000Gauss	520mW/cm ³ Max
Hi-Pot	1.5KVac,0.5mA, 3 sec	PASS

DC Bias Curves

